ASTM A515 Gr. 60

Pressure vessel plate

EQUIVALENT GRADES

India (IS)	AM/NS and Jindal Steel A515
USA (ASTM / AISI / SAE)	ASTM A515 / ASME SA515 Gr. 60
Europe (EN)	P265GH (nearest)
Japan (JIS)	SB410 (nearest)
China (GB)	Q245R (nearest)

CHEMICAL COMPOSITION (WEIGHT %)

C	Mn	Si	P
max 0.24	**max 0.98**	**0.13–0.45**	**max 0.025**

S
max 0.025

PROPERTIES

Mechanical (typical)	Tensile 415–550 MPa | Yield min 220 MPa | Elongation min 25% (50 mm)
Density	7.85 g/cm3 (7,850 kg/m3)
Typical uses	Mostly used for boilers and pressure vessels in intermediate and higher-temperature service
Notes	Carbon limit rises with thickness. Coarse-grain (Si-killed) practice, unlike fine-grain A516 for low-temperature service.

SUPPLY

Enquiry	Send grade, product form, size, quantity and delivery location for a quotation. Mill test certificates as per order.
Online	Equivalents, full chemistry by standard and weight calculator: https://steelimp.com/astm-a515-gr-60-equivalent-grades

Steel Impex India
231/235 Chouhan House, 2nd Kumbharwada Lane, Sant Sena Maharaj Marg, Mumbai, Maharashtra 400004, India

Tel: +91 95946 66986
sanjay@steelimp.com
Enquiry: steelimp.com/quote.php

Reference values compiled from published standards. Confirm against the governing standard, product form and the mill test certificate. Generated 12 Nov 2026.