IS 2062 E600

Structural steel

EQUIVALENT GRADES

India (IS)	IS 2062 E600
Europe (EN)	S600MC (nearest)
China (GB)	Q620 (nearest)

CHEMICAL COMPOSITION (WEIGHT %)

C	Mn	Si	P
max 0.22	**max 1.70**	**max 0.50**	**max 0.025**

S	Note
max 0.020	**CE max 0.54**

PROPERTIES

Mechanical (typical)	Tensile min 730 MPa | Yield min 600 MPa (<20 mm) | Elongation min 12%
Density	7.85 g/cm3 (7,850 kg/m3)
Typical uses	Mostly used for high-strength structural members and vehicle chassis parts
Notes	Equivalents are nearest only. Only A and BR qualities.

SUPPLY

Enquiry	Send grade, product form, size, quantity and delivery location for a quotation. Mill test certificates as per order.
Online	Equivalents, full chemistry by standard and weight calculator: https://steelimp.com/is-2062-e600-equivalent-grades

Steel Impex India
231/235 Chouhan House, 2nd Kumbharwada Lane, Sant Sena Maharaj Marg, Mumbai, Maharashtra 400004, India

Tel: +91 95946 66986
sanjay@steelimp.com
Enquiry: steelimp.com/quote.php

Reference values compiled from published standards. Confirm against the governing standard, product form and the mill test certificate. Generated 13 Nov 2026.

STEEL IMPEX INDIA

steelimp.com | +91 95946 66986 | sanjay@steelimp.com

REFERENCE-USE NOTICE

The toolkit may contain errors. Manually verify dimensions, calculations and specifications against the applicable standard and supplier documentation before purchase, fabrication or use.

Read this notice with the source, material, condition and scope notes accompanying the preceding grade datasheet.

231/235 Chouhan House, 2nd Kumbharwada Lane, Sant Sena Maharaj Marg, Mumbai, Maharashtra 400004, India